

Substrate temperature should be between 65° F (18°C) and 90°F (32°C).

MIXING

Ready to use; no mixing required

Note: Choose all appropriate safety equipment before use. Refer to Material Safety Data Sheet (MSDS) for more information.

PRODUCT APPLICATION

- Read all installation instructions thoroughly before installation.
- Refer to the wood-flooring manufacturer's guidelines for acclimation requirements and complete installation instructions.
- Remove the clip-on trowel attachments found inside the pail. See chart below to select proper trowel.
- Using a generous amount of adhesive, key the adhesive into the subfloor using the flat side of the trowel forming a continuous film of adhesive.
- Once the adhesive has been keyed in, immediately spread the adhesive using the provided clip-on trowel. Trowel ridge lines should be perpendicular to the wood-flooring installation direction. Hold the trowel at a 60° to 90° angle to the subfloor, making sure that the subfloor is covered 100% with adhesive and no void spots appear other than the "valley bottoms" created by the trowel. These areas will fill in as the wood is installed.
- Only apply as much adhesive as can be installed in 45 minutes.
- Install flooring in strict accordance with the flooring manufacturer's written instructions.
- Install the wood flooring immediately, pressing firmly into the adhesive to ensure 100% coverage of the subfloor and transfer to the wood flooring backing.
- Roll with 100 pound roller to insure wood is totally seated into the adhesive.
- Do not reuse clip-on trowel attachments.
- Protect from light traffic for at least 12 hours. Protect from heavy traffic for at least 24 hours.

CLEANUP

Clean any adhesive smudges *immediately* using a solvent-based urethane cleaner. Clean while adhesive is still fresh or wet.

NOTE: Green Earth Wood-Flooring Adhesive is extremely difficult to remove when cured. **Do not use water to remove adhesive or adhesive residue.**

PROTECT FROM FREEZING

Freeze/thaw-stable up to 5 cycles at 0°F (18°C). Store at room temperature in a dry area.

PRODUCT PROPERTIES

Polymer type	Moisture-cured Polyurethane
Percent solids	100%
VOCs (Rule #1168 of California's SCAQMD)	< 20 g/L
Odor	Light and sweet
Density	14 lbs. per U.S. gal. (1,69 g per mL)
Color	Light Brown