

Flash point (Tag)	> 200°F (93°C)
Shelf life	1 year when stored in original, unopened package at 73°F (23°C)
Perm rate (ASTM E96)	<0.15 perm

ASTM Standards for Sound Reduction: The following sound tests (for tile and wood flooring) were conducted and results supplied by NGC Testing Services, Buffalo, NY.

Sound-Reduction Ratings – Engineered Wood 3/8" (10 mm) Thick Over 6" (15 cm) Concrete Slab

ASTM Test Method	No Suspended Ceiling	Suspended Gypsum Ceiling
ASTM E90-09/E413-04 (STC) Airborne sound	50 (NGC Test No: 5010020)	67 (NGC Test No: 5010019)
ASTM E492-09/E989-09 (IIC) Impact Sound	50 (NGC Test No: 7010034)	68 (NGC Test No: 7010037)
ASTM E2179-03 (Delta IIC) Impact Sound	21 (NGC Test No: 7010035)	N/A

Trowels and Coverage: For Moisture or Sound Control and Crack Suppressant Warranty

For any questions, call the La Olden Information Center at [318-481-1969](tel:318-481-1969)

Flooring Type	Trowel	Coverage
For wood flooring > 3/8" (10 mm) and < 3/4" (19mm) in thickness:	3/8"x 3/16"x 3/8"x1/16" (10 x 4,5x10x1,5 mm) V-notch with spacers	30 sq. ft. per U.S. gal
For wood flooring less than < 3/8" (10mm) in thickness:	1/8"x1/8"x 1/8"x 1/16" (3x3x3x1,5 mm) V-notch with spacers	36 sq. ft. per U.S. gal

Trowels and Coverage: For Adhesive Bond Only

For any questions, call the La Olden Information Center at [318-481-1969](tel:318-481-1969)

Flooring Type	Trowel	Coverage
multi-ply engineered plank 3/8" up to 1/2" and 5/16" to 3/8" solid strip	3/16" X 1/4" on 1/2" Centers V Notch	50-60 sq. ft. per U.S. gal
5/16" solid parquet, 1/4"		70-80 sq. ft. per U.S. gal